

METAL PIGMENT COMPOSITION

The present invention relates to a process for preparing low- or non-dusting,
5 substantially non-volatile metal pigment compositions by a milling process using
a non-hydrocarbon milling fluid.

The preparation of metal flake pigments is well documented in the patent
literature. Metal flakes can be prepared in the complete absence of solvent by a
10 dry ball milling process, but this can be hazardous in the case of reactive metals
such as the widely employed aluminium, due to the contaminating and/or
explosive properties of the dry flake products.

Wet ball milling processes are also known in which metal powder or chopped foil
15 is milled with an organic liquid such as mineral spirits and a small amount of a
lubricant. However, the solvent portion of such metal pigment pastes is
especially disadvantageous in printed films on packaging intended for food
contact and the presence of organic solvent can also cause bubbles and surface
blemishes in the pigmented plastic articles. It is also found that the storage
20 stability of metal pigment pastes themselves is limited, due to the tendency of the
organic solvent component to evaporate, leading to aggregation of the metal
flake particles.

Environmental concern over volatile organic solvents in industrial processes has
25 led to pressure for their elimination from metal flake pigment manufacturing
processes and products and requires expensive equipment for solvent capture.

The need for a stable, safe and easily handled metal pigment product form has
been met by the products of European Patent 0134676B1. There is described
30 therein a process for the preparation of a solid, low- or non-dusting, metal
pigment composition, which comprises forming a coherent paste of an organic

binder medium, an organic liquid vehicle and metal pigment, in powder or flake form. The coherent paste is either sub-divided into particles and substantially all the organic liquid removed, or substantially all the organic liquid vehicle is removed from the coherent paste and the resulting mass sub-divided into
5 particles.

The problem of metal flake dusting may be reduced if the metal powder precursor is milled in the presence of a suitable organic carrier material. However, methods traditionally used to separate wanted from unwanted particle size fractions, such
10 as dilution with solvent, followed by wet screening, are then no longer operable at the dilutions necessary for efficient separation.

At first sight, water appears to be a more satisfactory processing liquid. It is readily available, inexpensive and non-flammable. However, a difficulty arises in
15 the case of the more reactive metal pigments, especially aluminium, which is the most widely used of such pigments. Finely divided aluminium metal may react with water to form aluminium oxide and hydrogen gas and the pigmentary properties of the metal flake are destroyed.

20 In European Patent 0934365B1 there is described the milling of aluminium powder in a milling fluid consisting substantially of water, in the presence of one or more additives, which together exhibit lubricating, corrosion inhibiting and surfactant properties. The milled material is subsequently converted into a low-or non-dusting, substantially non-volatile, metal flake pigment composition.
25 However, the unpredictability of the aluminium reaction with water means that product integrity cannot always be guaranteed. There therefore remains a need for a fully satisfactory, commercially viable process that can be used to prepare aluminium and other metal pigments in the substantial absence of both water and hydrocarbon solvents, whilst affording appropriate covering power, opacity, gloss
30 and other desirable properties of metal flake pigments and preserving the stability of the product.

Thus, according to the present invention, there is provided a process for preparing a low volatility metal flake pigment composition, which comprises milling metal powder in a non-aqueous, non-hydrocarbon milling fluid, optionally
5 in the presence of one or more substances that act as a lubricant and/or corrosion inhibitor. By non-hydrocarbon is meant an organic liquid that contains elements such as oxygen or nitrogen, in addition to hydrogen and carbon.

In one aspect the process comprises milling a mixture consisting of metal powder
10 and a non-aqueous, non-hydrocarbon, low volatility milling fluid and optionally one or more of a binder, corrosion inhibitor and/or lubricant.

After milling, unwanted oversize or undersize particles may be removed, for example by screening, before the metal pigment slurry is concentrated to a metal
15 flake pigment paste of typically 50 to 90% metal by weight. Such a paste may be sold as prepared, or may desirably be converted into a non-dusting, easily meterable granule form (also known as pellets).

To prepare the latter, an organic binder may be incorporated in the metal pigment
20 paste by mixing, optionally at elevated temperature, to form a coherent paste of organic binder, milling fluid and metal flake pigment. The paste, which typically contains from 3 to 70% of organic binder, based on the weight of the metal flake, may be sub-divided into particles, each containing a plurality of metal pigment particles dispersed and bound in a matrix of organic binder and milling fluid.
25 Preferably, at least 98% by weight of the particles are retained on a sieve having a 150 μ m aperture. If desired, part or all of the milling fluid may be removed at elevated temperature, for example to improve granule integrity.

There is a considerable commercial advantage through reduced stockholding if
30 one product can be employed satisfactorily in both solvent-based and water-based coatings and potentially also in mass-pigmented plastics. Such a metal

flake pigment product is obtained if a milling fluid is used that is not only both solvent and water miscible, but acts as a plasticiser in plastics. Such fluids are desirably also of low toxicity and odour, but also substantially non-volatile at ambient temperature, thereby limiting losses to atmosphere during manufacture, storage and use. Aggregation of metal flakes, due to fluid loss by evaporation, which causes reduced aesthetic performance, is also thereby avoided. Low volatility extends to the application. For example, in inks or paints, the milling fluid may be substantially retained in the coating, rather than being lost to atmosphere in the conventional drying of such coatings. Certain milling fluids may also be substantially retained in thermoplastics at their processing temperature.

Another advantage of the process of the present invention is the ability to treat the milled flakes whilst in the milling fluid. This may be for a variety of purposes. For example, to improve stability in aqueous application media, phosphates, aluminium or silicon compounds, such as silica or alumina, or chromates, such as ammonium dichromate, may be employed during or after milling. Other treatments, such as with ammonium or potassium permanganate, may be used to provide coloration of the flake surface, for example to simulate gold. Still further treatments may improve the hardness and therefore the shear resistance of such flakes in application media. There can be benefits in the properties of the finished particles if a thermal post-treatment is applied after the milling step.

The product of the milling step may be added to surface coating binders dissolved or dispersed in water, solvent or mixtures of the two, to prepare a surface coating, such as an ink or paint. The reaction of certain metal flake pigments, notably aluminium, is, however unpredictable. Where such a surface coating contains a proportion of water, there exists the possibility that reactions may occur during storage, with the formation of hydrogen gas with the aforementioned hazards. It is therefore desirable to passivate the metal flake during its preparation, through the addition of one or more corrosion inhibiting agents to the milling system.

The milling fluid of the present invention should comply with the following highly desirable requirements, plus as many desirable characteristics as possible.

5 Highly desirable requirements are that the milling fluid is:-

- of low viscosity; < 100cP, for instance <50cP, preferably less than 20cP, and especially of the order of 10cP or even below at 25°C. Too high a viscosity may extend the milling time, thereby increasing the cost of production.
- liquid in the temperature range of 10-40°C normally encountered in metal pigment manufacture,
- chemically unreactive with the metal pigment being prepared. This could eliminate halogen groups, which may react violently with certain metals in finely divided form, unless in the presence of a corrosion inhibitor.
- of low odour,
- of low toxicity,
- of low vapour pressure, ideally below 1mm Hg at 25°C and preferably below 0.1 mm Hg at 25°C. This characteristic limits losses to atmosphere through evaporation and helps to prevent the resulting aggregation of the paste product.

Desirable characteristics of the milling fluid include:-

- optical transparency,
- zero odour,
- non-flammability,
- non-classification for supply and transport by the EU and other jurisdictions.

Milling fluids suitable for the process of the invention are low-medium molecular weight alcohols, glycols, ethers and esters, plus certain ketonic species and hetero atom-containing compounds.

5 Amongst alcohols there may be mentioned pentyl and hexyl alcohols, 2(2-n-butoxy ethoxy ethanol), tetrahydropyran and tetrahydropyran-2-methanol, whilst glycols may comprise, amongst others, ethylene glycol, dimethylene glycol, diethylene glycol, trimethylene glycol, triethylene glycol, propylene glycols, butylene glycols and glycerol.

10

Gamma butyrolactone, 2-pyrrolidone, N-methyl pyrrolidone, isophorone, triacetin, 2,5,hexanedione, tetraethylene pentamine, triethyl phosphate, ethyl acetoacetate and n-methyl formamide may have utility in some systems. Propylene carbonate is also suitable.

15

Also suitable for the process of the invention are the lower mono and dialkyl ethers, esters and mixed ether esters of mono-, di- and tri- ethylene and propylene glycols. Examples of ethers are ethylene glycol monobutyl ether, diethylene glycol monomethyl, monoethyl, monopropyl and monobutyl ethers, 20 triethylene glycol monomethyl, monoethyl, monopropyl and monobutyl ethers, diethylene glycol dimethyl, diethyl, dipropyl and dibutyl ethers, triethylene glycol dimethyl, diethyl, dipropyl and dibutyl ethers, propylene glycol monobutyl ether, dipropylene glycol monomethyl, monoethyl, monopropyl and monobutyl ethers, tripropylene glycol monomethyl, monoethyl, monopropyl and monobutyl ethers, 25 dipropylene glycol dimethyl, diethyl, dipropyl and dibutyl ethers, and tripropylene glycol dimethyl, diethyl, dipropyl and dibutyl ethers. Diamyl ether may also be used.

Examples of esters and mixed ether esters are methoxypropyl acetate, ethylene 30 glycol monobutyl ether acetate, diethylene glycol monomethyl ether acetate, diethylene glycol monoethyl ether acetate, diethylene glycol monobutyl ether

acetate, dipropylene glycol monomethyl ether acetate and propylene glycol diacetate. Methyl, ethyl and propyl lactate plus the monomethyl, monoethyl, dimethyl and diethyl esters of succinic, glutaric and adipic acids may also be used. Mixtures of any of the above milling liquids may be used.

5

Aforementioned compounds displaying low nominal water solubility may yet be suitable in water-based application systems because they may act as bridging solvents where there is also some water-miscible organic solvent present in the formulation.

10

Particularly preferred are propylene carbonate, dipropylene glycol dimethyl ether, commercially available as Dow Proglyde DMM, (Dow Proglyde DMM is a trademark of the Dow Chemical Company), diethylene glycol monoethyl ether acetate, sold as DE Acetate (Eastman DE acetate is a trade name of the Eastman Chemical Company), dipropylene glycol n-propyl ether, sold as Dowanol DPnP, (Dowanol DPnP is a trade name of the Dow Chemical Company), tripropylene glycol methyl ether, sold as Dowanol TPM, (Dowanol TPM is a trade name of the Dow Chemical Company), diethylene glycol monobutyl ether acetate, sold by Union Carbide Corporation as butyl Carbitol acetate, (Carbitol is a trademark of the Union Carbide Corporation), a mixture of dimethyl esters of adipic, glutaric and succinic acids, supplied by DuPont under the trade name DBE.

Metals suitable for the performance of the invention include all those metals and alloys commercially employed as flake pigments, such as aluminium, zinc, copper, tin, nickel, silver, gold, iron and alloys thereof, such as gold bronze, an alloy of copper and zinc, or stainless steel, an alloy composed mainly of iron. Aluminium and gold bronze are preferred, as they have the greatest commercial potential. There is no criticality to the particle size of the milled flakes, but a median flake diameter range of 6µm to 600µm, preferably 10µm to 300µm, is generally suitable.

Although not essential to the performance of the invention, where the product of the invention is intended for use in water-based systems, it is desirable to include corrosion inhibitors in the comminution of the more chemically reactive metals, such as aluminium. Any compounds capable of inhibiting the reaction of the metal with water may be employed as corrosion inhibitors. Examples are phosphorus-, chromium-, vanadium-, molybdenum-, tungsten-, zirconium-, titanium- or silicon-containing compounds and heteropolyanionic compounds thereof. They may be used individually or in admixture, with addition before, during or after milling.

Suitable phosphorus compounds may be organic or inorganic. Simple inorganic phosphates, such as calcium or magnesium phosphate, or more complex phosphosilicate compounds may be used. The latter include calcium phosphosilicate, calcium strontium phosphosilicate and aluminium zirconium zinc phosphosilicate. An especially preferred member of this class is calcium strontium zinc phosphosilicate.

Organic phosphorus compounds include alkyl and dialkyl phosphates, phosphates, phosphonic acids and their derivatives. Such alkyl and dialkyl groups may contain 1-20 carbon atoms. Iso-octyl acid phosphate, octyl phosphonic acid, lauryl phosphonic acid, and lauryl phosphate may be particularly mentioned. Also especially suitable are phosphate esters of long chain ethoxylated alcohols.

Silicon containing compounds capable of inhibiting the reaction of metals with water include organic silanes and silicates, especially tetra ethyl silicate and inorganic silicon compounds such as potassium silicate.

Compounds of molybdenum, vanadium, titanium and tungsten, especially molybdic acid, some ammonium salts and alkaline and alkaline earth salts, have also shown particular suitability in the process of the invention.

- 5 Chromium compounds that may be employed in the invention include ammonium dichromate and chromic acid. In this class, the former is preferred as it is less aggressive towards metal grinding media.

10 Amongst the above corrosion inhibiting compounds, non-resinous organic or inorganic phosphates are especially preferred. They generally offer a high level of corrosion resistance, with few health and safety concerns.

Long chain fatty acids, especially stearic and oleic acids, have traditionally been used as lubricants in the conventional hydrocarbon solvent-based milling process. Such lubricants are generally added at a few percent by weight, calculated on the metal weight. They have the effect of preventing cold welding of incipient metal flakes under the action of the milling media. It is an advantage of the present invention that certain milling fluids do not require the addition of a lubricant. Apart from avoidance of lubricant cost, the collection and reuse of solvent is thereby facilitated. Where there is advantage in their use, lubricants suitable for the process of the invention are generally organic compounds recognised in the art as having both lubrication properties and imparting corrosion resistance and/or adhesion properties in application. Amongst those compounds imparting particularly good adhesion properties are mineral oils, also known as white oils, which are hydrocarbons having boiling points in the range of 180 to 300°C.

The corrosion inhibitor and milling lubricant functions may be advantageously provided by a single chemical substance, for example a phosphated ester of ethoxylated alcohols. Alternatively the functions may be provided by two or more

different materials. Such compounds may also improve adhesion to the substrate when the products of the invention are used in coating applications.

5 There is no criticality to the mechanism of milling. Any comminution process known in the art for metal flake production may be employed, providing the mechanical energy imparted is not so severe as to damage the metal flakes being formed. Ball milling is a widely operated process.

10 Neither is there any criticality to the grinding media, providing they do not undergo undesirable chemical reactions with the other components during or after the comminution stage of the process. Steel, glass and high-density ceramic grinding media are generally satisfactory.

15 Unwanted oversize or undersize metal flake particles may be removed by any suitable means, such as screening of the milled slurry, optionally diluted by more milling fluid. The metal pigment slurry can then be concentrated to a paste by any convenient means, such as a filter press, ready for sale as a paste. Alternatively, it may be admixed with organic binder medium and formed into granules.

20 Organic binder media include those organic materials habitually employed as binders in paints and inks or as plastics masterbatch carriers. The organic binder chosen is dependent on the envisaged end use of the product of the invention. If the derived granules are to be capable of use in both water-based and solvent-based application systems, the organic binder should be compatible with both
25 systems. Many acrylic and related resins are solvent soluble, but become water soluble on neutralisation with a suitable amine.

Alternatively, if desired, the organic binder medium may specifically be a solvent-soluble resin. As examples of such media there may be mentioned cellulose
30 acetate butyrate (CAB) and cellulose acetate propionate (CAP) resins, coumarone indene, epoxy esters, epoxide melamine and epoxide phenolic

condensates, ketone, aldehyde, maleic and phenolic resins and also rosin, cellulose and petroleum derived resins, together with thermoplastic polymers, such as polyacrylates, polyolefins, polyvinyls, styrenics, polyamides, polyesters and copolymers thereof. Also suitable are natural and synthetic waxes, such as
5 montan and paraffin wax and synthetic waxes such as polyethylene and polypropylene waxes.

Where it is desired to introduce liquid organic binders, such as plasticisers, for example to improve application properties, they are desirably added in minor
10 proportions in combination with solid resins, to retain structural rigidity in the resulting granules. Such plasticisers include mineral oils as well as phthalates such as dioctyl or di-isodecyl phthalate, and adipates, such as dioctyl adipate.

Amongst organic binders suitable for water-based application systems, gelatin
15 and carrageenan may be mentioned. Some surfactants may also be used, though care must be taken that the adhesion of derived coatings to the application substrate is not impaired.

It is an advantage of the granule-forming stage of the process that it is not
20 generally necessary to pre-dissolve or pre-disperse organic binders in solvent. Indeed it may be undesirable to do so, as the viscosity may be reduced too much to provide granules of satisfactory structural integrity. Rather, dry organic binder may be added to the metal pigment paste, heating if necessary to achieve a homogenous mass, capable of formation into granules without substantial
25 removal of the milling fluid. In some applications, the presence of milling fluid may be undesirable. For example, the application properties of some printing inks may be adversely affected. In such cases the milling fluid may be removed at elevated temperature, optionally under vacuum.

30 Granular products of the invention are typically in a form such as tablet, pellet, granule, flake or spherical bead, which provides the attributes of ease of

handling, non-dusting and meterability. Granules having a length of 5 to 20mm, and a thickness of 1.5 to 3mm are preferred, as they have been found to offer optimum handling characteristics, especially in plastics applications where it is important to prevent stratification of polymer pellets and the more dense products of the invention. Apparatus used for the preparation of such physical forms is well known to those skilled in the art and is described in, for example, European Patent 0134676B1.

The function of the organic binder medium is to immobilise the metal pigment flakes to prevent them becoming airborne as dust. Where the organic binder medium is insoluble in the milling fluid, it may be preferable to micronise the binder, that is to say, reduce its particle size to the micron size range. In this latter case, the coherent paste of metal pigment, milling fluid and micronised organic binder medium is formed into particles, for example by mixing and extrusion, then heat treated at elevated temperature, for example 100 to 130°C for a short time, to fuse together the micronised organic binder medium and the metal flake pigment. This process is particularly suited to products for the plastics market, in which suitable organic binder media may be insoluble in the milling fluid. It provides a final product form that has excellent colouristic and application properties when used in the injection moulding or extrusion of thermoplastics.

The invention is further illustrated by the following Examples in which all parts and percentages are by weight, unless otherwise stated.

25

EXAMPLE 1

The following materials were added to a rigid cylindrical polypropylene container of volume one litre:

30

1607g of 3mm diameter stainless steel balls

207g of butyl Carbitol acetate

30g of aluminium powder of approximately 7 μ m median particle diameter

2.1g of oleic acid

- 5 The sealed container and contents were put on a vibratory mill. After three hours, the mill contents were removed and separated from the steel balls by sieving, prior to recovery by vacuum filtration using a Buchner funnel. The aluminium pigment flakes produced were then incorporated into both a solvent based and a water-based acrylic ink system and drawn down onto paper using a wire-wound
10 bar. A bright metallic appearance with good coverage was obtained in both ink systems.

EXAMPLE 2

- 15 The following mixture was milled for three hours in a vibratory mill, sieved and concentrated by vacuum filtration as described in Example 1:-

1607g of 3mm diameter stainless steel balls

- 20 207g of Proglyde DMM

30g of a fine aluminium powder of approx. 7 μ m median particle diameter

2.1g of Briphos S2D, a phosphated ester of ethoxylated C₁₂₋₁₅ alcohols, (Briphos is a trademark of Rhodia), which had been neutralised with triethanolamine.

- 25 The resulting pigment flakes were then incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright ink, with a good metallic appearance and good coverage was obtained in both ink systems.

- The corrosion resistance of this aluminium pigment was tested by measuring the
30 gas evolved when formulated in an acrylic coating system, Joncryl 537, and stored for one week at 52°C. (Joncryl 537 is a dispersion of an acrylic copolymer

in water. Joncryn is a trademark of S. C. Johnson & Son Inc.) The amount of gas evolved, for 10g of this metallic pigment (as solids) in 150g of Joncryn 537 and 50g of water was 8.6ml This indicated that the aluminium flake surfaces were well protected from reaction with water.

5

EXAMPLE 3

The following mixture was milled for three hours in a vibratory mill, sieved and concentrated by vacuum filtration as described in Example 1:-

10

1607g of 3mm diameter stainless steel balls

207g of Dowanol TPM

30g of aluminium powder of approx. 7 μ m median particle diameter

15

No lubricant was added to this mill formulation. The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright metallic ink, with good coverage was obtained in both systems.

20

EXAMPLE 4

The following mixture was milled for three hours in a vibratory mill, sieved and concentrated by vacuum filtration as described in Example 1:-

25

1607g of 3mm diameter stainless steel balls

207g of Eastman DE acetate

30g of aluminium powder of approximately 7 μ m median particle diameter

30

2.1g of stearic acid

The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright ink, with good coverage was obtained in both ink systems.

5

EXAMPLE 5

The following mixture was milled for three hours in a vibratory mill, sieved and concentrated by vacuum filtration as described in Example 1:-

10

1607g of 3mm diameter stainless steel balls

207g of butyl Carbitol acetate

30g of aluminium powder of approximately 7µm median particle diameter

2.1g of mineral oil

15

Mineral oil is a saturated hydrocarbon of low volatility, having a vapour pressure of approximately 0.001mm Hg.

The aluminium pigment flakes produced were incorporated into both solvent based and water based acrylic ink systems and drawn down. A bright metallic appearance ink, with a good coverage and good adhesion on a tape removal test was obtained in both ink systems.

25 EXAMPLE 6

The following mixture was milled for three hours in a vibratory mill, sieved and followed by pigment concentration by vacuum filtration as described in Example 1:-

30

1607g of 3mm diameter stainless steel balls

207g of DuPont DBE

30g of aluminium powder of approximately 7µm median particle diameter

2.1g of oleic acid

- 5 The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright metallic ink, with good coverage and good adhesion on a tape removal test was obtained in both systems.

10

EXAMPLE 7

The following mixture was milled for five hours in a vibratory mill, sieved and followed by pigment concentration by vacuum filtration as described in Example

15 1:-

1607g of 3mm diameter stainless steel balls

207g of Dowanol Proglyde DMM

60g of copper powder

20 2.1g of stearic acid

The resultant copper pigment flakes produced were then incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright copper coloured ink effect was obtained with both ink systems.

25

EXAMPLE 8

The following mixture was milled in a vibratory mill for five hours, sieved and
30 followed by pigment concentration by vacuum filtration. As in Example 1:-

1607g of 3mm diameter stainless steel balls
207g of Dowanol Proglyde DMM
60g of iron powder of approximate median diameter of 16µm
2.1g of oleic acid

5

The resultant pigment flakes produced were then incorporated into both a solvent based and a water based ink system. A metallic, gunmetal colour effect was obtained with both ink systems.

10

EXAMPLE 9

The following mixture was milled in a vibratory mill, sieved and concentrated by vacuum filtration as described in Example 1 :-

15

1607g of 3mm diameter stainless steel balls
207g of Dowanol TPM
30g of aluminium powder of median particle size of approximately 7 µm
2.1g of lauryl phosphate

20

The aluminium pigment flakes produced were then incorporated into a water based acrylic ink system and drawn down. A bright metallic effect ink, with good coverage was obtained.

25

EXAMPLE 10

The following mixture was milled in a vibratory mill, sieved and concentrated by vacuum filtration, as described in Example 1 :-

30

1607g of 3mm diameter stainless steel balls

207g of Eastman DE Acetate

30g of aluminium powder of median particle size of approximately 7 μ m

2.1g of octadecyl phosphonic acid

- 5 The aluminium pigment flakes produced were incorporated into both a solvent based and a water based ink system and drawn down. A bright metallic appearance ink, with good coverage was obtained in both systems.

10 **EXAMPLE 11**

The following mixture was milled in a vibratory mill sieved and concentrated by vacuum filtration as described in Example 1:-

- 15 1607g of 3mm diameter stainless steel balls

207g of Dupont DBE

30g of aluminium powder of median particle size of approximately 7 μ m

2.1g of lauryl phosphonic acid. Lauryl phosphonic acid was supplied by Rhodia.

- 20 The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright ink, with good coverage was obtained in both systems.

25 **EXAMPLE 12**

The following mixture was milled in a vibratory mill, sieved and concentrated by vacuum filtration, as described in Example 1:-

- 30 1607g of 3mm diameter stainless steel balls

207g of propylene carbonate

30g of aluminium powder of median particle size of approximately 7 μ m
2.1g of oleic acid

The aluminium pigment flakes produced were incorporated into both a solvent
5 based and a water based acrylic ink system and drawn down. A bright metallic
appearance ink, with good coverage was obtained in both systems.

EXAMPLE 13

10

The following mixture was milled for ten hours in a sealed, cylindrical pot of 30cm
diameter, set on revolving rollers. The resulting slurry was sieved and
concentrated by vacuum filtration as described in Example 1:-

15

3330g of 3mm diameter stainless steel balls
428.5g of Eastman DE acetate
62.2g of aluminium powder of approximately 7 μ m median particle diameter.

35.4g of this paste product, containing 20g of aluminium metal, was added to
20 5.0g Laropal K80 resin (BASF GmbH) and the mixture heated to 75°C for 30
minutes, with gentle stirring to provide a homogenous mixture. The mixture was
forced through a perforated mesh to give granules of approx. 10mm length and
2mm thickness.

25

The resultant granules were dispersed in an ethyl acetate-based acrylic ink
system by slow speed paddle stirring, then drawn down against the feed paste at
equal metal content, similarly dispersed. The drawdown showed that the
granulated material was very similar in appearance to the feed paste. The
physical form of the granule made it more easily handled than the paste.

30

EXAMPLE 14

The following mixture was milled in a vibratory mill for 6 hours, sieved and
5 concentrated by vacuum filtration as described in Example 1:-

1607g of 3mm diameter stainless steel balls
207g of Eastman DE acetate
30g of aluminium powder of median particle size of approximately 7 μ m
10 2.1g of oleic acid

15.2g of the thus formed aluminium paste, containing 10g of aluminium metal,
was added to 3.2g low molecular weight polyethylene wax granules and the
mixture heated at 100°C for 1 hour whilst gently mixing to provide a homogenous
15 mixture. The mixture was granulated and recovered as described in Example 13.

The resultant granules were incorporated at 1.0% by weight in polypropylene in
an injection-moulding machine held at approximately 220°C. The moulded
articles exhibited a smooth, uniformly pigmented, silver surface, with no obvious
20 defects. The granule was more easily handled than the feed paste.

EXAMPLE 15

The following mixture was milled in a vibratory mill for 3 hours as described in
25 Example 1, then sieved to remove the grinding media.

1607g of 3mm diameter stainless steel balls
207g of Dowanol DPnP
30g of aluminium powder of approximately 7 μ m median particle diameter
30 2.1g of oleic acid.

The resulting aluminium flake pigment slurry was then maintained at 110°C for 2 hours, then cooled and concentrated by filtration. The paste so formed, containing 10g of aluminium metal, was dispersed in 150g of Joncryl 537 and 50g of water. Corrosion resistance was tested by measuring the gas evolved
5 when formulated in this acrylic coating system and stored for one week at 52°C. The amount of gas evolved was 12.4ml. This indicated that the aluminium flake surfaces were well protected from reaction with water.

The paste product was also tested in water- and solvent-based paints, applied to
10 card by drawdown. A bright metallic appearance with good coverage was obtained in both systems.

EXAMPLE 16

15 The following mixture was milled for ten hours in a sealed, cylindrical pot of 30cm diameter, set on revolving rollers. The resulting slurry was sieved and concentrated by vacuum filtration as described in Example 1:-

1607g of 3mm diameter stainless steel balls
20 207g of Dowanol DPnP
30g of aluminium powder of approx. 10µm median particle diameter

No lubricant was added to this mill formulation. The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic
25 ink system and drawn down. A bright metallic ink, with good coverage was obtained in both systems.

35g of the thus formed aluminium paste, containing 20g of aluminium metal, were added to 3g of calcium strontium zinc phosphosilicate and mixed until
30 homogenous. The corrosion resistance of a quantity of this mixture containing 10g of aluminium metal was tested by measuring the gas evolved when

formulated in an aqueous acrylic coating system, Joncryl 537, and stored for one week at 52°C. The amount of gas evolved was 3.5ml. This indicated that the aluminium flake surfaces were well protected from reaction with water.

5

EXAMPLE 17

The following mixture was milled for ten hours in a sealed, cylindrical pot of 30cm diameter, set on revolving rollers. The resulting slurry was sieved and
10 concentrated by vacuum filtration as described in Example 1:-

3330g of 3mm diameter stainless steel balls

428.5g of Dowanol DPnP

62.2g of aluminium powder of approximately 7µm median particle diameter.

15

No lubricant was added to this mill formulation. The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright metallic ink, with good coverage was obtained in both systems.

20

35g of the thus formed aluminium paste, containing 20g of aluminium metal, were added to 200g Dowanol DPnP and the mixture stirred for 30 mins at 25°C. To the mixture was added 8g tetraethyl silicate and 20g of 25% ammonia solution. The mixture was allowed to stir for 16 hours and thereafter concentrated by vacuum
25 filtration.

The corrosion resistance of this aluminium pigment paste was tested by measuring the gas evolved when formulated in an aqueous acrylic coating system, Joncryl 537, and stored for one week at 52°C. The amount of gas
30 evolved, for 10g of this metallic pigment (as solids) in 150g of Joncryl 537 and 50g of water was 15ml. This indicated that the aluminium flake surfaces were well protected from reaction with water.

EXAMPLE 18

5 The following mixture was milled for ten hours in a sealed, cylindrical pot of 30cm diameter, set on revolving rollers. The resulting slurry was sieved to remove the grinding media.

3330g of 3mm diameter stainless steel balls
430g of Dowanol DPnP
10 62g of aluminium powder of approximately 7µm median particle diameter.
4.3g oleic acid

0.15g octyl phosphonic acid was added to the milling fluid and the resulting slurry heated with agitation to 100°C for 3hrs. The mixture was thereafter cooled and
15 concentrated by vacuum filtration.

The corrosion resistance of this aluminium pigment paste was tested by measuring the gas evolved when formulated in an acrylic coating system, Joncryl 537, and stored for one week at 52°C. The amount of gas evolved, for 10g of this
20 metallic pigment (as solids) in 150g of Joncryl 537 and 50g of water, was 12.5ml. This indicated that the aluminium flake surfaces were well protected from reaction with water.

EXAMPLE 19

25

The following mixture was milled for ten hours in a sealed, cylindrical pot of 30cm diameter, set on revolving rollers. The resulting slurry was sieved and concentrated by vacuum filtration as described in Example 1:-

30 3330g of 3mm diameter stainless steel balls
428.5g of dipropylene glycol n-propyl ether

62.2g of aluminium powder of approximately 7µm median particle diameter.

No lubricant was added to this mill formulation. The aluminium pigment flakes produced were incorporated into both a solvent based and a water based acrylic ink system and drawn down. A bright metallic ink, with good coverage was obtained in both systems.

35g of the thus formed aluminium paste, containing 20g of aluminium metal, was added to 200g dipropylene glycol n-propyl ether and the mixture stirred for 30 mins. Added dropwise to this mixture were 12g of a 50% solution of potassium permanganate in water. The mixture was stirred for a further 30 mins. A colour change from silver to gold was observed in the reaction slurry. The mixture was concentrated by vacuum filtration on a Buchner funnel.

15 **EXAMPLE 20**

The following mixture was milled for ten hours in a sealed, cylindrical pot of 30cm diameter set on revolving rollers. The resulting slurry was sieved and concentrated by vacuum filtration as described in Example 1:-

20

3330g of 3mm diameter stainless steel balls

428.5g of Dowanol TPM

62.2g of aluminium powder of approximately 7µm median particle diameter.

25 35.4g of this paste product, containing 20g of aluminium metal, were added to 8.5g of a low molecular weight polyethylene wax. This mixture was heated to 100°C for 30 minutes, with gentle stirring to provide a homogenous mixture. The mixture was forced through a perforated mesh to give granules of approx. 10mm length and 2mm thickness. The resulting granules, containing this mix of

aluminium pigment, low volatile solvent and polymer, were incorporated into polypropylene by injection moulding to form pigmented polyethylene plaques of excellent metallic appearance.